



# Moplen EP545L

Fully Formulated Polypropylene Impact Copolymer Resin

## Features

- Enhanced stiffness
- Resist dust and dirt pick-up
- Excellent strength
- High slip
- Short cycle time for high productivity

## Typical applications

- Closures
- Containers
- Toys

PP Resin Properties (a)	Value	ASTM METHOD(b)
Melt flow rate (230°C / 2.16 kg), dg/min	6.0	D1238
Density, g/cm <sup>3</sup>	0.90	D792B
Tensile strength at yield, MPa	31	D638
Elongation at yield, %	7.0	D638
Flexural modulus, MPa	1480	D790A
Notched izod impact strength at 23°C, J/m	77	D256A
Deflection temperature, at 455 kPa, °C	115	D648

(a) Values shown are averages and are not to be considered as specifications.

(b) ASTM test methods are the latest under the Society's current procedures. All molded specimens are prepared by injection molding.

Note: Due to the fact that different regulations in each country set different details of compliance, users of *Moplen* EP545L are recommended to undertake their own investigation of the requirements and comply with each regulation set forth, for instance, in applicable local F&DA requirements. Ultimately the users must make their own determination that their use of *Moplen* EP545L is safe, lawful and technically suitable in their intended applications.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

*Moplen* is a trademark of LyondellBasell Industries  
HMC Polymers is certified according to ISO 9001 and 14001  
Issued 20-Sep-10

**The purpose of this document is only for technical support of the use of the product.**

Before using a HMC Polymers product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the HMC Polymers product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under HMC Polymers', LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of HMC Polymers except in a writing signed by an authorized HMC Polymers employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at HMC Polymers' option, and in no event shall HMC Polymers be liable for special, consequential, or exemplary damages.

Southern Bangkok 10120, Thailand  
Tel +66 2614 3700 Fax +66 2679

6380

www.hmcpolymers.com

